

AMENDMENT TO THE CLAIMS

1. (Currently Amended) A pressure-sensitive adhesive sheet for skin adhesion, which comprises a substrate and an adhesive layer laminated on the substrate, wherein the adhesive layer is obtained by curing an adhesive composition comprising polyether polymer (A) having a number average molecular weight of 10000-30000 and at least one alkenyl group on the terminal, compound (B) having a number average molecular weight of 500-100 and 1 - 10 hydrosilyl groups in a molecule and hydrosilylation catalyst (C), and the molar ratio of the hydrosilyl group/alkenyl group is 0.3-0.8.

2. (Original) The pressure-sensitive adhesive sheet of claim 1, wherein the polymer (A) is a polyether polymer having an alkenyl group represented by the following formula (1) or (2),

(1) $\text{H}_2\text{C}=\text{C}(\text{R}^1)-$

(2) $\text{HC}(\text{R}^1)=\text{CH}-$

wherein R^1 is a hydrogen atom or a hydrocarbon group having 1 to 10 carbon atoms, and the catalyst (C) is a platinum complex that does not contain a conjugate base of a strong acid as a ligand.

3. (Original) The pressure-sensitive adhesive sheet of claim 2, wherein R^1 is a hydrogen atom or a methyl group.

4. (Previously Presented) The pressure-sensitive adhesive sheet of claim 2, wherein the platinum complex is a platinum-vinyl siloxane complex.

5. (Original) The pressure-sensitive adhesive sheet of claim 4, wherein the platinum-vinyl siloxane complex is a platinum-1,3-divinyl-1,1,3,3-tetramethyldisiloxane complex or a platinum-1,3,5,7-tetravinyl-1,3,5,7-tetramethylcyclotetrasiloxane complex.

6. (Previously Presented) The pressure-sensitive adhesive sheet of claim 1, wherein the main chain of the polymer (A) has a polyoxypropylene skeleton.

7. (Previously Presented) The pressure-sensitive adhesive sheet of claim 1, wherein the

polymer (A) has a number average molecular weight in polystyrene conversion of 3000 – 50000 as measured by size-exclusion chromatography.

8. (Previously Presented) The pressure-sensitive adhesive sheet of claim 1, wherein the proportion of the toluene-insoluble component in the adhesive layer is 10 - 50 wt%.

9. (Previously Presented) The pressure-sensitive adhesive sheet of claim 1, which has a moisture permeability of not less than $800 \text{ g/m}^2 \cdot 24 \text{ hr}$, as measured under the conditions of thickness of adhesive layer 50 μm , temperature 40°C and relative humidity 30%.

10. (Previously Presented) The pressure-sensitive adhesive sheet of claim 3, wherein the platinum complex is a platinum-vinyl siloxane complex.

11. (Previously Presented) The pressure-sensitive adhesive sheet of claim 10, wherein the platinum-vinyl siloxane complex is a platinum-1,3-divinyl-1,1,3,3-tetramethyldisiloxane complex or a platinum-1,3,5,7-tetravinyl-1,3,5,7-tetramethylcyclotetrasiloxane complex.